

## IIER - 767<sup>TH</sup> INTERNATIONAL CONFERENCE ON RECENT INNOVATIONS IN ENGINEERING AND TECHNOLOGY ICRIET, DOHA, QATAR, DECEMBER 10-11, 2019. (accepted version- May 12<sup>th</sup> 2019)

## FINITE ELEMENT THERMAL STRESS SIMULATION OF NANO-COATED GAS TURBINE BLADE SAMPLES UNDER HIGH TEMPERATURE

Ali Kadir<sup>1</sup>, O. Anwar Bég<sup>1</sup>, Tasveer A. Bég<sup>2</sup> and Walid S. Jouri<sup>1</sup> <sup>1</sup>Department of Mechanical/Aeronautical Engineering, Salford University, Manchester, M54WT, UK. <sup>2</sup> Renewable Energy and Computational Multi-Physics, Israfil House, Dickenson Rd., Manchester, M13, UK. Emails: A.Kadir@salford.ac.uk (Presenter); O.A.Beg@Salford.ac.uk; tasveerabeg@gmail.com; w.s.jouri@salford.ac.uk;

## **1.INTRODUCTION**

Several studies have been communicated in recent years considering nano-coating protective layers for gas turbine environments. They have generally shown that improved protection is achieved compared with conventional thermal barrier coatings (TBCs) which are susceptible to various life limiting issues associated with their operating environment including erosion, corrosion, oxidation, sintering and foreign object damage (FOD) [1,2]. Nano-coatings engineered for high temperature applications have been investigated for surface roughness and topography, residual stress, adherence, damage tolerance and resistance, tribological properties, lubrication, coefficient of friction and hot hardness. Motivated by these developments, in this presentation we describe recent finite element thermal stress simulations of nano-coated (Aluminium Oxide/Titanium Oxide metallic nano-particle mix). The simulations demonstrate that largely due to the higher thermal conductivity and smaller size of nano-particles, they achieve improved bonding in coatings and dissipate heat better than conventional micro-coatings. Greater integrity of the coating is achieved and lower susceptibility to corrosion gas penetration is obtained with nano-coatings compared with microcoatings. ANSYS Workbench version 19.1 [3] has been employed to simulate the thermal stress response of nano-coatings. Extensive visualization of results is included. Important deductions on nano-coating performance are made. The study provides a useful compliment to experimental tests which are also being conducted.

A three-dimensional model was created using the ANSYS static structural geometry modeller to represent a steel sample under high temperature corrosion. A two-layered domain in (x,y,z) space is created with the base layer representing the gas turbine blade substrate (AISI 304 super alloy) and the upper layer simulating the Alumina-Titanium oxide nano-coating, as shown below. Note the nano-coating completely engulfs the substrate specimen. The fixture (cylindrical hole) is also shown in order to compare simulations with future HVOF experiments. Below shows the front (top) and 3-D rendition of the model. The clamping is achieved via the hole which penetrates the entire substrate and is filled with nano-material during the coating process. The nano coating thickness is 0.816 mm. The substrate sample dimensions are 10.98mm (depth), 20.76mm (length) and width (186mm). The boundary conditions imposed on all six faces of the coated model is a thermal one due to the hot gas at an average temperature of 1000 °C. The structural boundary condition is the fixing hole where the model is constrained.



## **2. NANO-COATING PROPERTIES**

Since a continuum-based finite element approach is adopted, molecular variations in nano-particle dynamics in the coating cannot be simulated. Instead an *average value of materials properties* is adopted for a 60:40 % titanium oxide  $(TiO_2)$  : aluminium oxide  $(Al_2O_3)$  mix nano-coating (powder). The table below summarizes the key material properties (Young modulus, Poisson ratio, density and thermal conductivity) for the original nano—powders and the composite nano-coating:

Property	Steel	Titanium oxide	Alumina	Nano-coating
	(AISI 304 Superalloy)	(nano-powder)	(Aluminium oxide nano-powder)	Alumina-Titanium Oxide 60:40 mix
Young Modulus	200GPa	288 GPa	413GPa	363 GPa
Poisson Ratio	0.28	0.29	0.33	0.314
Density	7850kg/m <sup>3</sup>	4050kg/m <sup>3</sup>	3980 kg/m <sup>3</sup>	4008 kg/m <sup>3</sup>
Thermal conductivity	50W/mK	20W/mK	24W/mK	9.6W/mK



# **3. ANSYS THERMAL STRESS FORMULATION**



## **4. ANSYS MESH AND THERMAL STRESS ANALYSIS**

N.B. In ANSYS workbench, the data is usually supplied as a mean value and this data is correctly used by ANSYS, if T<sub>REE</sub> is not only the definition temperature about which the data is supplied but also the reference temperature at which zero strains exist. Mesh independence was tested for. A default mesh of 140,000 elements was found to achieve grid independent results. The nano-coating simulations are compared with micro-coated steel samples using a single Titanium thermal barrier coating layer also engulfing the sample with 1mm depth, performed in an earlier study [4].



### Equivalent strain -60:40 Alumina-Titanium oxide nano-coating versus micro-coated titanium case



Total deformation plot for 60:40 Alumina-Titanium oxide nano-coating versus micro-coated titanium case

## **5. CONCLUSIONS**

In all cases the nano-coating is found to provide superior thermal protection to the steel substrate (AISI 304 super alloy). High stress zones are completely eliminated with nano-coating whereas they are prevalent with titanium micro-coating. Although titanium oxide has excellent thermal resistance properties, the alumina nano-powder when mixed with titania, produces an inert performance which is and resistant to inter-diffusion and this leads to stability during exposure to elevated temperatures for long periods of time, thus preserving the sharp interface and minimizing thermal stresses which are necessary for good thermal barrier performance. The alumina material tends to form an amorphous structure when it is deposited onto a substrate which is held at a relatively low temperature and in the alternative it tends to form a crystalline structure when applied by a vapor deposition to a substrate held at a relatively high temperaturesubstrate. Either case will result in a very resilient nano-coating which achieves excellent bonding to the super alloy substrate and prevents the penetration of hot gas since at the nanoscale cracks of micro-scale magnitude are mitigated. This is not possible in the micro-coating which flakes, permits heat penetration, has reduced integrity and eventually cracks. Alumina being integral to the coating layer and in contact with the substrate has the desirable characteristic that since the native oxide which forms on the substrate due to oxidation of the substrate will be alumina, therefore having a nano-structured alumina layer in the coating adjacent to a naturally occurring alumina layer will probably provide the best coating adherence as noted in [2]. Overall much lower stresses, strains and deformations are produced with nano-coatings

## REFERENCES

[1] N.B. Dahotre and S. Nayak, Nanocoatings for engine application, *Surface and Coatings Technology*, 194, 58-67 (2005).

[2] C.G. Zhou and Q.H. Yu, Nanostructured thermal barrier coatings, Thermal Barrier Coatings, Woodhead Publishing Series in Metals and Surface Engineering, 75-96 (2011).

[3] ANSYS Theory Manual, ver 19.1, (Thermal stress analysis theory) Swanson Analysis Systems, Pittsburgh, USA (2018).

[4] Ali Kadir and O. Anwar Bég, Thermal stress and computational fluid dynamics analysis of coatings for high-temperature corrosion, ICHTFM 2018: 20th International Conference on Heat Transfer and Fluid Mechanics, Istanbul, Turkey, August 16 –